

# AF 75 PLUS

## Technical sheet

Recommended use : Flexible windows

Characteristics	Values		Units	Standards
	Warp	Weft		
<b>General characteristics</b>				
Thickness	0.75		mm	ISO 5084
Coating	PVC			
Finish	Transparent Anti UV			
Weight	915		g/m <sup>2</sup>	ISO 3801
Light transmission	92		%	
Width	140		cm	
Roll length	30		ml	

## Fabric resistance

Flexibility	46		PHR	
Tensile strength	25.4	22.1	N/mm <sup>2</sup>	ASTM D 882-02
Elongation at break	300	310	%	ASTM D 882
Dimensional stability	2		%	10 min / 50°
Dimensional stability	4.5		%	ASTM D 1204-02 (10 min / 80°)
Weather resistance	PASS			ASTM D1499 (Xenotest: 2000 hours)
Cold resistance	-20		°C	ASTM D 1790



## AnsonFabrics Co.

No.36 Fenghuang Road  
Qianjiang Industry Zone  
Haining, 314413  
82.5730.5258  
(customer service)  
86.182.5832.6285

INFO@ANSONFABRICS.COM

