

AF 900

Technical sheet

Recommended use : Warehouses



Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Base cloth	1100 dTex PES HT 990 den			
Coating	PVC coating both side			
Finish	Cleangard lacquer both sides			
Weight	900		g/m ²	ISO 3801
Width	300	300	cm	
Roll length	60	200	ml	
Fabric resistance				
Tensile strength	400	400	daN/5cm	NF EN ISO 1421
Tear strength	60	50	daN	DIN 53.363
Adhesion	10		daN/5cm	NF EN ISO 2411
Elongation under load	<1	<2	%	NF EN 15619
Residual deformation	<0.4	<0.8	%	NF EN 15619
Cold resistance	-40		°C	NF EN 1876-1
Warm resistance	70		°C	[24h]
Fire resistance	M2			NF P 92 503
	B1			DIN 4102
	BS			BS 7837
	B-s2-d0			Euroclasses EN 13501-1
	NFPA 701			NFPA 701
	CSFM Title19			CSFM Title 19



AnsonFabrics Co.

No.36 Fenghuang Road
Qianjiang Industry Zone
Haining, 314413
82.5730.5258
(customer service)
86.182.5832.6285
INFO@ANSONFABRICS.COM

