

AF-BLOCKLIGHT

Technical sheet

Recommended use : Terrace awnings, Pergolas, Awnings, Small structures, Glamping, Sail shade

Comments : 100% OPAQUE

Characteristics	Values				Units	Standards
	Warp		Weft			
General characteristics						
Base cloth	550 dTex PES HT					
	495 den					
Coating	PVC coating both side					
Finish	Cleangard lacquer both sides					
Weight	640				g/m ²	ISO 3801
Width	250	250	300	300	cm	
Roll length	30	60	30	60	ml	

Fabric resistance

Tensile strength	150	150	daN/5cm	NF EN ISO 1421
Tear strength	15	15	daN	DIN 53.363
Adhesion	7		daN/5cm	NF EN ISO 2411
Elongation under load	<1	<3	%	NF EN 15619
Residual deformation	<0.4	<0.8	%	NF EN 15619
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)
	M2			NF P 92 503



AnsonFabrics Co.

No.36 Fenghuang Road
 Qianjiang Industry Zone
 Haining, 314413
 82.5730.5258
 (customer service)
 86.182.5832.6285
 INFO@ANSONFABRICS.COM

