

AF 640

Technical sheet

Recommended use : Tarpaulins for agriculture, Covers and lagging, Trailers, Over top covers

| Characteristics | Values | | Units | Standards |
|--------------------------------|------------------------------|------|------------------|-----------|
| | Warp | Weft | | |
| General characteristics | | | | |
| Base cloth | 1100 dTex PES HT 990 den | | | |
| Coating | PVC coating both side | | | |
| Finish | Cleangard lacquer both sides | | | |
| Weight | 640 | | g/m ² | ISO 3801 |
| Width | 150 250 250 300 300 320 320 | | cm | |
| Roll length | 60 60 250 60 250 60 250 | | ml | |

Fabric resistance

| | | | | |
|------------------|-------|-----|---------|-----------------|
| Tensile strength | 220 | 210 | daN/5cm | NF EN ISO 1421 |
| Tear strength | 30 | 25 | daN | DIN 53.363 |
| Adhesion | 8 | | daN/5cm | NF EN ISO 2411 |
| Cold resistance | -30 | | °C | NF EN 1876-2 |
| Warm resistance | 70 | | °C | (24h) |
| Fire resistance | < 100 | | mm/min | DIN 75 200 |
| | < 100 | | mm/min | ISO 3795 : 1989 |



AnsonFabrics Co.

No.36 Fenghuang Road

Qianjiang Industry Zone

Haining, 314413

82.5730.5258

(customer service)

86.182.5832.6285

INFO@ANSONFABRICS.COM

