

# AF 901 BC

## Technical sheet

Recommended use : Tarpaulins for agriculture, Truck side curtains, Over top covers, Flexible doors

Comments : Complies with : EN 12641-2

Characteristics	Values		Units	Standards
	Warp	Weft		
<b>General characteristics</b>				
Base cloth	1100 dTex PES HT			
	990 den			
Coating	PVC coating both side			
Finish	Cleangard lacquer both sides			
Weight	900		g/m <sup>2</sup>	ISO 3801
Width	300 300 300 314 314 314		cm	
Roll length	30 60 200 30 60 200		ml	

## Fabric resistance

Tensile strength	400	400	daN/5cm	NF EN ISO 1421
Tear strength	60	50	daN	DIN 53.363
Adhesion	10		daN/5cm	NF EN ISO 2411
Puncture resistance	8		kN	NF EN 12236
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)
Fire resistance	< 100		mm/min	DIN 75 200
	< 100		mm/min	ISO 3795 : 1989



AnsonFabrics Co.

No.36 Fenghuang Road

Qianjiang Industry Zone

Haining, 314413

82.5730.5258

(customer service)

86.182.5832.6285

INFO@ANSONFABRICS.COM

