

AF COVERLAC

Technical sheet

Recommended use : Swimming pool cover

Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Base cloth	1100 dTex PES HT 990 den			
Coating	PVC coating both side			
Finish	Cleangard lacquer both sides			
Weight	700		g/m ²	ISO 3801
Width	300	300	cm	
Roll length	60	250	m	

Fabric resistance

Tensile strength	220	210	daN/5cm	NF EN ISO 1421
Tear strength	30	25	daN	DIN 53.363
Adhesion	8		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)



AnsonFabrics Co.

No.36 Fenghuang Road
Qianjiang Industry Zone
Haining, 314413

82.5730.5258
(customer service)

86.182.5832.6285

INFO@ANSONFABRICS.COM

