

# AF ECO 640

## Technical sheet

Recommended use : Over top covers

Comments : PVC is composed of recycled paste (top-side grey 7196 : RAL 7037, and the reverse-side can vary)

Characteristics	Values		Units	Standards
	Warp	Weft		
<b>General characteristics</b>				
Base cloth	1100 dTex PES HT 990 den			
Coating	PVC coating both side			
Finish	Cleangard lacquer both sides			
Weight		640	g/m <sup>2</sup>	ISO 3801
Width	300	300	cm	
Roll length	60	250	ml	

## Fabric resistance

Tensile strength	220	210	daN/5cm	NF EN ISO 1421
Tear strength	30	25	daN	DIN 53.363
Adhesion	8		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	[24h]
Fire resistance	< 100		mm/min	DIN 75 200



## AnsonFabrics Co.

No.36 Fenghuang Road  
Qianjiang Industry Zone  
Haining, 314413  
82.5730.5258  
(customer service)  
86.182.5832.6285  
INFO@ANSONFABRICS.COM

