

# AF UNI540

## Technical sheet

Recommended use : Trailers, Tarpaulins for agriculture, Over top covers, Covers and lagging

Characteristics	Values		Units	Standards
	Warp	Weft		
<b>General characteristics</b>				
Base cloth	1100 dTex PES HT 990 den			
Coating	PVC coating one side			
Finish	Cleangard lacquer both side			
Weight	s	540	g/m <sup>2</sup>	ISO 3801
Width	300	300	cm	
Roll length	60	250	ml	

## Fabric resistance

Tensile strength	220	210	daN/5cm	NF EN ISO 1421
Tear strength	25	20	daN	DIN 53.363
Adhesion	8		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)
Fire resistance	< 100		mm/min	DIN 75 200



## AnsonFabrics Co.

No.36 Fenghuang Road  
Qianjiang Industry Zone

Haining, 314413

82.5730.5258

(customer service)

86.182.5832.6285

INFO@ANSONFABRICS.COM

