

HX 580

Technical sheet

Recommended use : Reinforcements

Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Base cloth	1100 dTex PES HT 990 den			
Coating	PVC coating both side			
Finish	Cleangard lacquer both sides			
Weight	580		g/m ²	ISO 3801
Width	250		cm	
Roll length	125		m	

Fabric resistance

Tensile strength	220	210	daN/5cm	NF EN ISO 1421
Tear strength	30	25	daN	DIN 53.363
Adhesion	9		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)



AnsonFabrics Co.

No.36 Fenghuang Road
Qianjiang Industry Zone

Haining, 314413

82.5730.5258

(customer service)

86.182.5832.6285

INFO@ANSONFABRICS.COM

