

JET 560

Technical sheet

Recommended use : Banners, Signage, Pole banners

Range :

Printing : digital inkjet printing

Printable side : Outside

Ink : Solvent, Eco-solvent, UV, Latex Ink

| Characteristics | Values | | Units | Standards |
|--------------------------------|-----------------------------------|------|------------------|-----------|
| | Warp | Weft | | |
| General characteristics | | | | |
| Thickness | 0.47 | | mm | ISO 5084 |
| Base cloth | 1100 dTex PES HT 990 den | | | |
| Coating | PVC coating one side | | | |
| Finish | Inkjet lacquer one side | | | |
| Weight | 560 | | g/m ² | ISO 3801 |
| Translucency | 6 | | % | XPT 54199 |
| Width | 76 106 137 162 250 250 320 320 | | cm | |
| Roll length | 30 30 30 30 30 60 30 60 | | mL | |

Fabric resistance

| | | | | |
|------------------|----------|-----|---------|----------------|
| Tensile strength | 210 | 200 | daN/5cm | NF EN ISO 1421 |
| Tear strength | 25 | 20 | daN | DIN 53.363 |
| Adhesion | 7 | | daN/5cm | NF EN ISO 2411 |
| Cold resistance | -30 | | °C | NF EN 1876-2 |
| Warm resistance | 70 | | °C | [24h] |
| Fire resistance | < 100 | | mm/min | DIN 75 200 |
| | NFPA 701 | | | NFPA 701 |



AnsonFabrics Co.

No.36 Fenghuang Road

Qianjiang Industry Zone

Haining, 314413

82.5730.5258

(customer service)

86.182.5832.6285

INFO@ANSONFABRICS.COM

