

AF 1250 CTM

Technical sheet

Recommended use : Retention pond, Flexible Tank, Slurry pit covering

Comments : Specially designed formulation for chemical resistance to acids and alkalis present in agricultural slurry. Good hydrolysis resistance.

Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Base cloth	1100 dTex PES HT 990 den			
Coating	PVC coating both side			
Finish	Cleangard lacquer both sides			
Weight		1250	g/m ²	ISO 3801
Width	300	300	cm	
Roll length	60	200	ml	

Fabric resistance

Tensile strength	420	420	daN/5cm	NF EN ISO 1421
Tear strength	60	60	daN	DIN 53.363
Adhesion	14		daN/5cm	NF EN ISO 2411
Puncture resistance	8		kN	NF EN 12236
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)



AnsonFabrics Co.

No.36 Fenghuang Road

Qianjiang Industry Zone

Haining, 314413

82.5730.5258

(customer service)

86.182.5832.6285

INFO@ANSONFABRICS.COM



RESOURCE

