

AF 950 CTM

Technical sheet

Recommended use : Slurry pit covering, Flexible Tank

Characteristics	Values		Units	Standards
	Warp	Weft		
General characteristics				
Base cloth	1100 dTex PES HT 990 den			
Coating	PVC coating both side			
Finish	Cleangard lacquer both sides			
Weight	950		g/m ²	ISO 3801
Width	300	300	cm	
Roll length	60	200	ml	

Fabric resistance

Tensile strength	400	400	daN/5cm	NF EN ISO 1421
Tear strength	50	50	daN	DIN 53.363
Adhesion	12		daN/5cm	NF EN ISO 2411
Puncture resistance	8		kN	NF EN 12236
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)



AnsonFabrics Co.

No.36 Fenghuang Road
Qianjiang Industry Zone

Haining, 314413

82.5730.5258

(customer service)

86.182.5832.6285

INFO@ANSONFABRICS.COM



RESOURCE

