

JET 550 FR

Technical sheet

Recommended use : Separation curtains, Banners, P.O.S, Signage, Stand

Range : Frontlit

Printing : digital inkjet printing

Printable side : Outside

Ink : Solvent, Eco-solvent, UV, Latex Ink

| Characteristics | Values | | Units | Standards |
|--------------------------------|-----------------------------|------|------------------|-----------|
| | Warp | Weft | | |
| General characteristics | | | | |
| Thickness | 0.45 | | mm | ISO 5084 |
| Base cloth | 1100 dTex PES HT 990 den | | | |
| Coating | PVC coating one side | | Inkjet | |
| Finish | lacquer one side | | | |
| Weight | 550 | | g/m ² | ISO 3801 |
| Translucency | 6 | | % | XPT 54199 |
| Width | 106 137 162 250 320 | | cm | |
| Roll length | 30 30 30 60 60 | | ml | |

Fabric resistance

| | | | | |
|------------------|---------|-----|---------|---------------------------|
| Tensile strength | 210 | 200 | daN/5cm | NF EN ISO 1421 |
| Tear strength | 25 | 20 | daN | DIN 53.363 |
| Adhesion | 7 | | daN/5cm | NF EN ISO 2411 |
| Cold resistance | -30 | | °C | NF EN 1876-2 |
| Warm resistance | 70 | | °C | (24h) |
| Fire resistance | B-s2-d0 | | | Euroclasses EN 13501-1 |



ansonfabrics



AnsonFabrics Co.

No.36 Fenghuang Road
Qianjiang Industry Zone
Haining, 314413
82.5730.5258
(customer service)
86.182.5832.6285
INFO@ANSONFABRICS.COM



RESOURCE

